

MEDIUM	NR	NBR	SBR	EPDM	CR	FPM	MVQ	IIR	AU	CSM	PTFE
VINYLCETAT	-	D	-	B	-	D	-	B	-	-	A
VINYLCHELOIDE, WASSRIG	D	D	D	-	D	B	-	D	-	D	A
WALRATÖL (SPERMÖL)	D	A	D	D	B	A	-	D	-	D	A
WASSER BIS 100°C	B	B	B	A	A	A	B	A	D	A	A
WASSER BIS 80°C	A	B	A	A	A	A	A	A	D	A	A
WASSER DESTILLIERT, 50°C	B	B	B	A	B	B	B	A	D	A	A
WASSER, KALT	A	A	A	A	A	A	A	A	B	A	A
WASSER, SEEWASSER	A	A	A	A	A	A	A	A	D	A	A
WASSERSTOFFGAS, HEISS	D	B	D	A	A	A	-	A	-	A	A
WASSERSTOFFGAS, KALT	B	A	A	A	A	A	-	A	A	A	A
WASSERSTOFFSUPEROXID, 90 %	D	D	D	B	B	B	-	B	-	B	A
WEINSAURE	A	A	A	A	A	A	A	A	-	A	A
WOLLFETT	D	A	D	D	B	A	B	D	A	B	A
XYLOL	D	D	D	D	D	B	D	D	D	D	A
ZINKCHLORID	B	B	B	A	A	A	A	A	-	A	A
ZINKSULFAT	A	A	A	A	A	A	A	A	-	A	A
ZINNCHLORID	B	A	B	A	A	A	A	A	-	A	A
ZITRONENSAURE	A	B	B	A	A	A	A	A	-	A	A
ZUCKERRÜBENSAFT	A	A	A	A	A	A	A	A	-	A	A